

August 1, 2014

**Class 5000 Structural Concrete**

Subsection 701.2.12.2 Materials – Concrete Mix Design – Structural Concrete Table, of the 2007 Standard Specifications is amended to add Note 6 below to the Class 5000 Concrete shown in the Structural Concrete Table.

Note 6:

The maximum water to cementitious material ratio for Class 5000 concrete regardless of coarse aggregate type is 0.40 when air entrainment is required per 2007 Standard Specification Subsection 701.2.5 – Air Entrained Concrete.